


**1-15. (cancelled).**

**16. (currently amended):** A stabilizer mixture comprising a component a) and a component e)  
where

component a) is a compound of the formula



where


$\text{R}_1$  is hydrogen or methyl,

$\text{R}_2$  is  $\text{C}_1$ - $\text{C}_{10}$ alkylene,

$n_1$  is a number from 2 to 50,

and

component e) is a compound of the formula



where  $n_5$  is 1 to 20, and

where the weight ratio between component a) and component e) is about 20:1 to about 1:20.

- 17. (previously presented):** A stabilizer mixture according to claim **16**, wherein the weight ratio between component a) and component e) is from 5:1 to 1:5.
- 18. (previously presented):** A stabilizer mixture according to claim **16**, wherein the weight ratio between component a) and component e) is 1:1.
- 19. (previously presented):** A stabilizer mixture according to claim **16**, wherein  $R_1$  is hydrogen,  $R_2$  is ethylene and  $n_1$  is a number from 2 to 25.
- 20. (previously presented):** A composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a stabilizer mixture according to claim **16**.
- 21. (previously presented):** A composition according to claim **20**, in which the organic material is a polyolefin.
- 22. (previously presented):** A composition according to claim **20**, in which the organic material is polyethylene, polypropylene or a copolymer of polyethylene or polypropylene.
- 23. (previously presented):** A process for stabilizing an organic material which is sensitive to oxidative, thermal or light-induced degradation, which comprises incorporating a stabilizer mixture according to claim **16** into the organic material.
- 24. (previously presented):** A composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a stabilizer mixture according to claim **19**.

**25. (previously presented):** A composition according to claim **24**, in which the organic material is a polyolefin.

**26. (previously presented):** A composition according to claim **24**, in which the organic material is polyethylene, polypropylene or a copolymer of polyethylene or polypropylene.

**27. (previously presented):** A process for stabilizing an organic material which is sensitive to oxidative, thermal or light-induced degradation, which comprises incorporating a stabilizer mixture according to claim **19** into the organic material.